

HOP

This is a wet laid nonwoven fabric of 100% polyolefinic material. The seal temperature of 140°C. (The heat seal temperature may vary depending on conditions.)

No chemicals are used, and this heat adhesion fabric can be applied to foods and medical products.

【Features】	【Applications】	【Product Name】
<ul style="list-style-type: none">▪ Heat-seal property▪ High oil absorption▪ Good for heat-forming▪ High electric insulating property▪ High chemical resistance	<ul style="list-style-type: none">▪ Waterproofed sheet for medical use▪ Sterilized paper▪ Bags for dryers and deodorants▪ Papers for processing▪ Kitchen drain bags	<p>Type HOP-30H Weight g/m²</p>

サンプル物性値(Sample Properties)

品名	坪量 (Weight)	厚さ (Thickness)	密度 (Density)	引張強さ(Tensile strength) N/15mm		破断伸び(Stretch at break) %		通気度 (Air Permeability)
				MD	CD	MD	CD	
HOP-10H	9.72	47	0.207	8.49	4.54	12.5	12	299.7
HOP-30H	30.1	115	0.263	29.92	13.86	14.8	14.5	115.6
HOP-60HCF(170)	61	163	0.374	54.03	35.02	17.2	16.4	35.79

※上記データは実測値であり保証値ではございません。

ラインナップ(Lineup)	
HOP	30H
	60HCF

ご希望のタイプございましたら、遠慮なく、ご連絡ください。
A4サイズのサンプルをお送りいたします。

左表ラインナップは、定量的に出ている製品です。
物性値は調整も可能ですので、ご希望ございましたら、
ご相談ください。

If any of these grades could be of your interests, please do not
hesitate to contact us for any help. We will send you
A4(297mm x 210mm) size handsheets upon your request.

Lefthand side table shows product lineup that we regularly
produce certain quantity. Property values can be modified in
response to your request. Please feel free to consult with us for
such customization needs.

HIGH PERFORMANCE WET LAID NON-WOVEN PRODUCT

HIROSE

廣瀬製紙株式会社

高知県土佐市高岡町乙3292番地1

TEL 088-852-7771

FAX 088-852-7773

HIROSE PAPER MFG.CO.,LTD

3292-1 OTSU,TAKAOKA-CHO,TOSA-SHI,

KOCHI 781-1102,JAPAN

PHONE 81-88-852-7771

FAX 81-88-852-7773