

VN

VN is a very unique wet laid nonwoven fabric of 100% vinylon fiber. When infusible vinylon fibers are made into paper by fusible vinylon fiber binders, they are melted by a dryer and adhered strongly.

【Features】	【Applications】	【Product Name】
<ul style="list-style-type: none">▪ High tensile strength▪ High chemical resistance(alkali)▪ High corrosion resistance▪ Very tough and high abrasion resistance▪ High oil resistance▪ High heat resistance	<ul style="list-style-type: none">▪ Battery separator▪ Plywood reinforcing materials▪ Materials for construction works	<p>Type VN1012 Weight g/m²</p>

サンプル物性値(Sample Properties)

品名	坪量 (Weight)	厚さ (Thickness)	密度 (Density)	引張強さ(Tensile strength) N/15mm		破断伸び(Stretch at break) %		通気度 (Air Permeability)
				MD	CD	MD	CD	
VN1012	12.6	48	0.261	12.1	4.13	6.9	7.2	143.9
VN1048	47.9	153	0.313	78.54	37.6	10.8	11	26.85
VN10100	101.5	296	0.343	121.66	110.34	14.2	11.4	45.93

※上記データは実測値であり保証値ではございません。

ラインナップ(Lineup)	
VN	1012
	1024
	1036
	1048
	1060
	1084
	10100

ご希望のタイプございましたら、遠慮なく、ご連絡ください。
A4サイズのサンプルをお送りいたします。

左表ラインナップは、定量的に出ている製品です。
物性値は調整も可能ですので、ご希望ございましたら、
ご相談ください。

If any of these grades could be of your interests, please do not
hesitate to contact us for any help. We will send you
A4(297mm x 210mm) size handsheets upon your request.

Lefthand side table shows product lineup that we regularly
produce certain quantity. Property values can be modified in
response to your request. Please feel free to consult with us for
such customization needs.

HIGH PERFORMANCE WET LAID NON-WOVEN PRODUCT

HIROSE

廣瀬製紙株式会社

高知県土佐市高岡町乙3292番地1

TEL 088-852-7771

FAX 088-852-7773

HIROSE PAPER MFG.CO.,LTD

3292-1 OTSU,TAKAOKA-CHO,TOSA-SHI,

KOCHI 781-1102,JAPAN

PHONE 81-88-852-7771

FAX 81-88-852-7773